

Technical data sheet
Membrana mdm[®] Ventia Platinum Plus

Characteristic	Test method	Unit	Result	Tolerance	
				Min.	Max.
Length	EN 1848 -2	m	50	0	+0,5
Width	EN 1848 -2	m	1,5	-0,005	+0,005
Straightness	EN 1848 -2	-	Pass	-	-
Mass per unit area	EN 1848 -2	g/m ²	225	-10	+10
Thickness	EN 1848 -2	mm	0,9	-0,15	+0,15
Reaction to fire	EN 11925-2	class	E-d2	-	-
Resistance to water penetration	EN 1928 A	class	W1	-	-
Water vapour transmission Properties	EN ISO 12572 C	m	0,020	-0,005	+0,02
Resistance to penetration of air	EN 12114	m ³ /(m ² x h x 50 Pa)	Max 0,05	-	-
Tensile properties: Maximum tensile force	EN 12311-1	N/50mm	MD 460	-95	+95
			CD 320	-85	+85
Tensile properties: elongation	EN 12311-1	%	MD 75	-45	+45
			CD 105	-45	+45
Resistance to tearing (nail shank)	EN 12310-1	N	MD 220	-65	+65
			CD 265	-100	+100
Dimensional Stability	EN 1107-2	%	2	-	-
Stability at low temperature	EN 1109	°C	-40	-	-
Artificial ageing by long term exposure to the combination Of UV radiation and elevated Temperature and heat (80°C)	Elongation EN 13859-1 annex C	%	MD 50	-25	+25
			CD 60	-35	+35
	Tensile strength EN 13859-1 annex C	N/50mm	MD 410	-85	+85
			CD 245	-50	+50
Resistance to water penetration EN 13859-1 annex C	class	W1	-	-	
Water vapour transmission 23°C/85%RH	Lyssy	g/m ² x 24h	1300	-200	+200
Water vapour transmission 38°C/90%RH	Lyssy	g/m ² x 24h	2800	-400	+500

The above product technical data sheet is valid from 01.01.2019

Bielsko-Biała, 8.06.2018
 (Place and date of issue)